






## DELIVERY PROGRAMME

### Sheets & Plates



Sheets, cold-rolled, finish 2B	1 – 2
Sheets, cold-rolled, finish 2R	3
Sheets, hot-rolled, finish 1D	4 – 7
Sheets, hot rolled, heat resisting	8 – 9
Tear plates hot rolled	10 – 12
Pattern rolled sheets	13 – 14
Pattern rolled sheets	15
Perforated plates	16 – 18
Embossed plates	19
Technical Information	20



**Sheets, cold-rolled**

Type of finish 2 B

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN 10259 (formerly DIN 59382)

APZ EN 10204/3.1B or AD W2000

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571	W.-Nr. 1.4435
1000 x 2000 x	0,3	4,8	•	•	•		
	0,4	6,4	•	•	•		
	0,5	8,0	•	•	•		•
	0,6	9,6	•	•			•
	0,7	11,2	•	•	•	•	
	0,8	12,8	•	•	•	•	•
	1,0	16,0	•	•	•	•	•
	1,2	20,0	•	•	•	•	
	1,5	24,0	•	•	•	•	•
	2,0	32,0	•	•	•	•	•
	2,5	40,0	•	•	•	•	•
	3,0	48,0	•	•	•	•	•
	4,0	64,0	•	•	•	•	•
5,0	80,0	•	•	•	•	•	
6,0	96,0	•	•	•	•	•	

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571	W.-Nr. 1.4435
1250 x 2500 x	0,4	10,0	•				
	0,5	12,5	•				
	0,6	15,0	•				
	0,7	17,5	•				
	0,8	20,0	•	•	•	•	•
	1,0	25,0	•	•	•	•	•
	1,2	31,2	•	•	•	•	
	1,5	37,5	•	•	•	•	•
	2,0	50,0	•	•	•	•	•
	2,5	62,5	•	•	•	•	•
	3,0	75,0	•	•	•	•	•
	4,0	100,0	•	•	•	•	•
	5,0	125,0	•	•	•	•	•
6,0	150,0	•	•	•	•	•	

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571	W.-Nr. 1.4435
1500 x 3000 x	0,8	28,8	•	•	•	•	
	1,0	36,0	•	•	•	•	•
	1,2	45,0	•	•	•	•	
	1,5	54,0	•	•	•	•	•
	2,0	72,0	•	•	•	•	•
	2,5	90,0	•	•	•	•	•
	3,0	108,0	•	•	•	•	•
	4,0	144,0	•	•	•	•	•
	5,0	180,0	•	•	•	•	•
6,0	216,0	•	•	•	•	•	



**Sheets, cold-rolled**

Type of finish 2 B

Grit 180 and coated on one side with film

Grit 240 and coated on one side with film

Grit 320 and coated on one side with film

Brushed and coated on one side with film

Or only one side with film

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN 10259 (formerly DIN 59382)

APZ EN 10204/3.1B or AD W2000

size	thickness	plate kg	1.4301 180er Korn	1.4301 240er Korn	1.4301 320er Korn	1.4301 gebürstet	1.4301 ein. Folie
1000 x 2000 x	0,5	8,0	•	•	•	•	
	0,6	9,6	•	•	•	•	
	0,7	11,2	•	•	•	•	
	0,8	12,8	•	•	•	•	•
	1,0	16,0	•	•	•	•	•
	1,2	20,0	•	•	•	•	•
	1,5	24,0	•	•	•	•	•
	2,0	32,0	•	•	•	•	•
	2,5	40,0	•	•	•	•	•
	3,0	48,0	•	•	•	•	•
4,0	64,0	•	•	•	•	•	
5,0	80,0	•	•	•	•	•	

size	thickness	plate kg	1.4301 180er Korn	1.4301 240er Korn	1.4301 320er Korn	1.4301 gebürstet	1.4301 ein. Folie
1250 x 2500 x	0,8	20,0	•	•	•	•	•
	1,0	25,0	•	•	•	•	•
	1,2	31,2	•	•	•	•	•
	1,5	37,5	•	•	•	•	•
	2,0	50,0	•	•	•	•	•
	2,5	62,5	•	•	•	•	•
	3,0	75,0	•	•	•	•	•
	4,0	100,0	•	•	•	•	•
5,0	125,0	•	•	•	•	•	

size	thickness	plate kg	1.4301 240er Korn	1.4301 240er Korn	1.4301 320er Korn	1.4301 gebürstet	1.4301 ein. Folie
1250 x 3000 x	0,8	28,8	•	•	•	•	•
	1,0	36,0	•	•	•	•	•
	1,2	45,0	•	•	•	•	•
	1,5	54,0	•	•	•	•	•
	2,0	72,0	•	•	•	•	•
	2,5	90,0	•	•	•	•	•
	3,0	108,0	•	•	•	•	•
	4,0	144,0	•	•	•	•	•
5,0	180,0	•	•	•	•	•	



**Sheets, cold-rolled**

Type of finish 2 R

Type of finish 2 R and coated on one side with film

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN 10259 (formerly DIN 59382)

APZ EN 10204/3.1B

size	thickness	plate kg	1.4301 2 R	1.4301, 2 R + 100 my Folie	1.4016 2 R	1.4016, 2 R + 100 my Folie
1000 x 2000 x	0,3	4,8	•		•	
	0,4	6,4	•		•	
	0,5	8,0	•	•	•	•
	0,6	9,6	•	•	•	•
	0,7	11,2	•	•	•	•
	0,8	12,8	•	•	•	•
	1,0	16,0	•	•	•	•
	1,2	20,0	•	•	•	•
	1,5	24,0	•	•	•	•
	2,0	32,0	•	•	•	•
2,5	40,0	•	•	•	•	
3,0	48,0	•	•	•	•	

size	thickness	plate kg	1.4301 2 R	1.4301, 2 R + 100 my Folie	1.4016 2 R	1.4016, 2 R + 100 my Folie
1250 x 2500 x	0,4	10,0	•			
	0,5	12,5	•	•		•
	0,6	15,0	•	•		
	0,7	17,5	•	•		
	0,8	20,0	•	•	•	•
	1,0	25,0	•	•	•	•
	1,2	31,2	•	•	•	•
	1,5	37,5	•	•	•	•
	2,0	50,0	•	•	•	•
3,0	75,0	•	•	•	•	

size	thickness	plate kg	1.4301 2 R	1.4301, 2 R + 100 my Folie	1.4016 2 R	1.4016, 2 R + 100 my Folie
1500 x 3000 x	0,8	28,8	•	•	•	•
	1,0	36,0	•	•	•	•
	1,2	45,0	•	•	•	•
	1,5	54,0	•	•	•	•
	2,0	72,0	•	•	•	•
	3,0	108,0	•	•	•	•



**Plates, hot-rolled**

Type of finish 1 D

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN10051 and DIN EN 10029

APZ EN 10204/3.1B or AD W2000

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571
1000 x 2000 x	3,0	48,0	•	•	•	•
	4,0	64,0	•	•	•	•
	5,0	80,0	•	•	•	•
	6,0	96,0	•	•	•	•
	8,0	128,0	•	•	•	•
	10,0	160,0	•	•	•	•
	12,0	192,0	•	•	•	•
	15,0	240,0	•	•	•	•
	20,0	320,0	•	•	•	•
	25,0	400,0	•	•	•	•
	30,0	480,0	•	•	•	•
40,0	640,0	•	•	•	•	

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571
1250 x 2500 x	3,0	75,0	•	•	•	•
	4,0	100,0	•	•	•	•
	5,0	125,0	•	•	•	•
	6,0	150,0	•	•	•	•
	8,0	200,0	•	•	•	•
	10,0	250,0	•	•	•	•
	12,0	300,0	•	•	•	•
	15,0	375,0	•	•	•	•
	20,0	500,0	•	•	•	•
	25,0	625,0	•	•	•	•
	30,0	750,0	•	•	•	•

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571
1500 x 3000 x	3,0	108,0	•	•	•	•
	4,0	144,0	•	•	•	•
	5,0	180,0	•	•	•	•
	6,0	216,0	•	•	•	•
	8,0	288,0	•	•	•	•
	10,0	360,0	•	•	•	•
	12,0	432,0	•	•	•	•
	15,0	540,0	•	•	•	•
	20,0	720,0	•	•	•	•
	25,0	900,0	•	•	•	•
	30,0	1080,0	•	•	•	•
	40,0	1440,0	•	•	•	•
	50,0	1800,0	•	•	•	•



**Plates, hot-rolled**

Type of finish 1 D

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN10051 and DIN EN 10029

APZ EN 10204/3.1B or AD W2000

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571
2000 x 4000 x	5,0	320,0	•	•	•	•
	6,0	384,0	•	•	•	•
	8,0	512,0	•	•	•	•
	10,0	640,0	•	•	•	•
	12,0	768,0	•	•	•	•

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4404	W.-Nr. 1.4571
2000 x 6000 x	5,0	480,0	•	•	•	•
	6,0	576,0	•	•	•	•
	8,0	768,0	•	•	•	•
	10,0	960,0	•	•	•	•
	12,0	1152,0	•	•	•	•
	15,0	1440,0	•	•	•	•
	20,0	1920,0	•	•	•	•
	25,0	2400,0	•	•	•	•
	30,0	2880,0	•	•	•	•
	40,0	3840,0	•	•	•	•
	50,0	4800,0	•	•	•	•



**Plates, hot-rolled**

Type of finish 1 D

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN10051 and DIN EN 10029

APZ EN 10204/3.1B or AD W2000

size	thickness	plate kg	W.-Nr. 1.4301	W.-Nr. 1.4541	W.-Nr. 1.4571
2500 x6000 x	3,0	360,0	•	•	•
	4,0	480,0	•	•	•
	5,0	600,0	•	•	•
	6,0	720,0	•	•	•
	8,0	960,0	•	•	•
	10,0	1200,0	•	•	•
	12,0	1440,0	•	•	•
	15,0	1800,0	•	•	•
	18,0	2160,0	•	•	•
	20,0	2400,0		•	•
	22,0	2640,0	•	•	•
	25,0	3000,0		•	•
	28,0	3360,0	•	•	•
	30,0	3600,0	•	•	•
	35,0	4200,0	•	•	•
	40,0	4800,0	•	•	•
	45,0	5400,0	•	•	•
50,0	6000,0	•	•	•	
55,0	6600,0		•	•	
60,0	7200,0	•	•	•	

size	thickness	plate kg	W.-Nr. 1.4828	W.-Nr. 1.4841	W.-Nr. 1.4878
2500 x6000 x	3,0	360,0	•	•	•
	4,0	480,0	•	•	•
	5,0	600,0	•	•	•
	6,0	720,0	•	•	•
	8,0	960,0	•	•	•
	10,0	1200,0	•	•	•
	12,0	1440,0	•	•	•
	15,0	1800,0	•	•	•
	18,0	2160,0	•	•	•
	20,0	2400,0		•	•
	22,0	2640,0	•		•
	25,0	3000,0	•	•	•
	28,0	3360,0	•		•
	30,0	3600,0	•	•	•
	35,0	4200,0	•		•
	40,0	4800,0	•	•	•
	45,0	5400,0	•		•
50,0	6000,0	•	•	•	
55,0	6600,0	•			
60,0	7200,0	•		•	



**Plates, hot-rolled**

Type of finish 1 D

DIN EN 10088-2 and DIN EN 10028-7

Measurements DIN EN10051 and DIN EN 10029

APZ EN 10204/3.1B or AD W2000

size	thickness	plate kg	W.-Nr. 1.4404	W.-Nr. 1.4462	W.-Nr. 1.4439	W.-Nr. 1.4529	W.-Nr. 1.4306
2500 x 6500 x	3,0	360,0	•	•	•		•
	4,0	480,0	•	•	•		•
	5,0	600,0	•	•	•	•	•
	6,0	720,0	•	•	•	•	•
	8,0	960,0	•	•	•	•	•
	10,0	1200,0	•	•	•	•	•
	12,0	1440,0	•	•	•	•	•
	15,0	1800,0	•	•	•	•	•
	20,0	2400,0	•	•	•	•	•
	25,0	3000,0	•	•	•	•	•
	28,0	3360,0	•	•	•	•	•
	30,0	3600,0	•	•	•	•	•
	35,0	4200,0	•	•	•		•
	40,0	4800,0	•	•	•		•
	45,0	5400,0	•	•	•		•
50,0	6000,0	•	•	•		•	
60,0	7200,0	•	•	•			





**Plates, hot-rolled**

Type of finish 1 D

Heat resistant

size	thickness	plate kg	W.-Nr. 1.4828	W.-Nr. 1.4841	W.-Nr. 1.4878
1000 x 2000 x	0,8	12,8			•
	1,0	16,0			•
	1,5	24,0			•
	2,0	32,0	•	•	•
	3,0	48,0	•	•	•
	4,0	64,0	•	•	•
	5,0	80,0	•	•	•
	6,0	96,0	•	•	•
	8,0	128,0	•	•	•
	10,0	160,0	•	•	•
	12,0	192,0	•	•	•
	15,0	240,0	•	•	•
	18,0	288,0	•	•	•
	20,0	320,0	•	•	•
25,0	400,0				
30,0	480,0				

size	thickness	plate kg	W.-Nr. 1.4828	W.-Nr. 1.4841	W.-Nr. 1.4878
1250 x 2500 x	0,8	20,0			•
	1,0	25,0			•
	1,5	37,5			•
	2,0	50,0	•	•	•
	3,0	75,0	•	•	•
	4,0	100,0	•	•	•
	5,0	125,0	•	•	•
	6,0	150,0	•	•	•
	8,0	200,0	•	•	•
	10,0	250,0	•	•	•
	12,0	300,0	•	•	•
	15,0	375,0	•	•	•
20,0	500,0			•	

size	thickness	plate kg	W.-Nr. 1.4828	W.-Nr. 1.4841	W.-Nr. 1.4878
1500 x 3000 x	1,5	54,0			•
	2,0	72,0	•	•	•
	3,0	108,0	•	•	•
	4,0	144,0	•	•	•
	5,0	180,0	•	•	•
	6,0	216,0	•	•	•
	8,0	288,0	•	•	•
	10,0	360,0	•	•	•
	12,0	432,0	•	•	•
	15,0	540,0	•	•	•
20,0	720,0	•	•	•	



**Plates, hot-rolled**

Type of finish 1 D

Heat resistant

size	thickness	plate kg	W.-Nr. 1.4713	W.-Nr. 1.4742	W.-Nr. 1.4762	W.-Nr. 1.4828	W.-Nr. 1.4841
2000 x 6000 x	3,0	288,0	•	•	•	•	•
	4,0	384,0	•	•	•	•	•
	5,0	480,0	•	•	•	•	•
	6,0	576,0	•	•	•	•	•
	8,0	768,0	•	•	•	•	•
	10,0	960,0	•	•	•	•	•
	12,0	1152,0	•	•	•	•	•
	15,0	144,0	•	•	•	•	•
	20,0	1920,0	•	•	•	•	•
	25,0	2400,0				•	
30,0	2880,0				•		



**Tear plates hot-rolled**

Type of finish 1 D and ASTM A

Mandorla/Floorplate/Nippon

DIN 59229 and DIN 51130

Anti slip class R11/V10 + R12/V8

size	thick-ness	plate kg	Mandorla		Floorplate		Nippon-Floor	
			1.4301	1.4571	1.4301	1.4571	1.4301	1.4404
1000 x 2000 x	2,5 + T	46,0	•				•	
1000 x 3000 x	2,5 + T	69,0	•				•	
1000 x 2000 x	3,0 + T	56,0	•	•			•	
1000 x 3000 x	3,0 + T	84,0	•	•	•		•	•
1000 x 4000 x	3,0 + T	112,0	•					
1250 x 2500 x	3,0 + T	88,0	•	•			•	
1250 x 3000 x	3,0 + T	105,0	•	•			•	
1500 x 3000 x	3,0 + T	138,0	•	•				
1000 x 2000 x	3,5 + T	64,0	•	•		•	•	•
1250 x 2500 x	3,5 + T	100,0	•	•	•		•	•
1250 x 3000 x	3,5 + T	120,0	•					
1500 x 3000 x	3,5 + T	148,0	•		•		•	
1000 x 2000 x	4,0 + T	74,0	•	•		•	•	
1000 x 3000 x	4,0 + T	112,0	•	•				
1250 x 2500 x	4,0 + T	116,0	•	•			•	
1250 x 3000 x	4,0 + T	139,0	•		•			
1500 x 3000 x	4,0 + T	160,0	•	•			•	
1500 x 6000 x	4,0 + T	320,0	•					
2000 x 4000 x	4,0 + T	280,0	•	•	•			
2000 x 6000 x	4,0 + T	440,0	•	•				
1000 x 2000 x	4,5 + T	81,0	•		•	•		
1250 x 2500 x	4,5 + T	126,0	•		•			
1250 x 3000 x	4,5 + T	152,0	•					
1250 x 5000 x	4,5 + T	250,0	•					
1250 x 6000 x	4,5 + T	300,0	•					
1500 x 3000 x	4,5 + T	175,0	•					
1000 x 2000 x	5,0 + T	89,0	•	•	•		•	
1250 x 2500 x	5,0 + T	140,0	•	•			•	
1250 x 3000 x	5,0 + T	167,0	•					
1250 x 5000 x	5,0 + T	280,0	•					
1250 x 6000 x	5,0 + T	330,0	•					
1500 x 3000 x	5,0 + T	190,0	•	•	•		•	
1500 x 6000 x	5,0 + T	380,0	•					
2000 x 4000 x	5,0 + T	340,0	•	•		•		
2000 x 6000 x	5,0 + T	540,0	•	•				



**Strutura**

Formed plates

Type of finish 2

size	thickness	plate kg	Strutura	
			1.4301	1.4401
1000 x 2000 x	1,0 + T	16,0		
1250 x 2500 x	1,0 + T	25,0	•	
1500 x 3000 x	1,0 + T	36,0	•	
1000 x 2000 x	1,5 + T	24,0	•	
1250 x 2500 x	1,5 + T	38,0	•	•
1500 x 3000 x	1,5 + T	54,0	•	•
1000 x 2000 x	2,0 + T	32,0		•
1250 x 2500 x	2,0 + T	50,0		
1500 x 3000 x	2,0 + T	72,0		•



**Pattern rolled stainless-steel sheet, cold rolled**

Brushed and one side coated


4301

Design 2WL 5WL 6WL 7WL

size	thickness	plate kg	2WL	5WL	6WL	7WL
1000 x 2000 x	0,5	8,0		•		•
1250 x 2500 x	0,5	12,5		•		•
1000 x 2000 x	0,6	9,6		•		
1250 x 2500 x	0,6	15,0		•		
1000 x 2000 x	0,8	12,8		•		•
1250 x 2500 x	0,8	20,0	•	•	•	•
1250 x 3000 x	0,8	24,0		•		•
1000 x 2000 x	1,0	16,0		•		
1250 x 2500 x	1,0	25,0	•	•	•	•
1250 x 3000 x	1,0	30,0		•		•
1000 x 2000 x	1,2	20,0		•		•
1250 x 2500 x	1,2	32,0		•	•	•
1250 x 3000 x	1,2	37,5				
				•		•
1000 x 2000 x	1,5	24,0		•		•
1000 x 3000 x	1,5	36,0				
1250 x 2500 x	1,5	37,5		•	•	•
1250 x 3000 x	1,5	45,0		•	•	•



2WL



5WL



6WL



**Design stainless-steel sheets, cold rolled**

Type 2 B

Decor sheets one side coated

4301

size	thickness	plate kg	Leder	Karo	Raute	Leinen
1000 x 2000 x	0,8	12,8			•	
1250 x 2500 x	0,8	20,0	•	•	•	•
1500 x 3000 x	0,8	28,8	•	•	•	•
1000 x 2000 x	1,0	16,0	•		•	
1250 x 2500 x	1,0	25,0	•	•	•	•
1500 x 3000 x	1,0	36,0	•	•	•	•
1250 x 2500 x	1,2	32,0			•	•
1250 x 3000 x	1,2	37,5				•
1500 x 3000 x	1,2	45,0	•	•		
1000 x 2000 x	1,5	24,0	•	•	•	
1250 x 2500 x	1,5	37,5	•	•	•	•
1500 x 3000 x	1,5	54,0	•		•	•
1250 x 2500 x	2,0	50,0		•		•

size	thickness	plate kg	Eisblume	Sandrelief	Feinkorn	
1250 x 2500 x	0,8	20,0	•	•	•	
1500 x 3000 x	0,8	28,8	•	•		
1000 x 2000 x	1,0	16,0				
1250 x 2500 x	1,0	25,0	•	•	•	
1500 x 3000 x	1,0	36,0	•	•		
1000 x 2000 x	1,2	20,0				
1250 x 2500 x	1,2	31,2	•			
1500 x 3000 x	1,2	45,0				
1000 x 2000 x	1,5	24,0	•			
1250 x 2500 x	1,5	37,5	•	•	•	
1500 x 3000 x	1,5	54,0	•	•		



**Design stainless-steel sheets, cold rolled**

Decor cirles

size	thickness	plate kg	W.-Nr. 1.4301
1000 x 2000 x	0,8	12,8	•
1250 x 2500 x	0,8	20,0	•
1500 x 3000 x	0,8	28,8	•
1000 x 2000 x	1,0	16,0	•
1250 x 2500 x	1,0	25,0	•
1500 x 3000 x	1,0	36,0	•
1000 x 2000 x	1,2	20,0	•
1250 x 2500 x	1,2	31,2	•
1500 x 3000 x	1,2	45,0	•
1000 x 2000 x	1,5	24,0	•
1250 x 2500 x	1,5	37,0	•
1500 x 3000 x	1,5	54,0	•
1000 x 2000 x	2,0	32,0	•
1250 x 2500 x	2,0	50,0	•
1500 x 3000 x	2,0	72,0	•




**Decor**



Square, big negative



Square, big positive



Chess



Circles



Square




Rhomb



Linen



Leather



Pearls



Frost work




Mite



Bricks



Letters



Pikee



Grain




7 GM






**Perforated plates**


Round, displaced




Rv 1,5 -2,5




Rv 2-3,5




Rv 3-4




Rv 3-6



Rv 3,5-6




Rv 4-5




Rv 4-8




Rv 5-8




Rv 6-8



Rv 6-9



Rv 8-10




RV 8-11




**Perforated plates**


Round, displaced




Rv 8-12




Rv 8-16




Rv 10-14




Rv 10-15




Rv 10-18



Rv 12-16




Rv 15-21




Rv 20-28

**Perforated plates**

Round, in line



Rg 4,5-15




Eurolochung




**Perforated plates**


square




Qg 4-7




Qg 5-8



Qg 10-12




Qg 10-15




Qg 15-20

**Perforated plates**


long



Lv 2-20



Lv 3-20



Lv 5-20




**Embossed plates**

Structur


Round and square

size	thick-ness	plate kg	Rg 10-30	Rg 12-40	Rg 15-36	Og 10-30	Og 15-40	Og 20-50
1000 x 2000 x	1,5	24,0	•	•	•	•	•	•
1250 x 2500 x	1,5	38,0	•			•	•	•

**round**



**square**





**Surface condition of sheets**

EN 10088

Production methods and surface condition

Product	EN 10088	Production method	surface condition	DIN 17 440 DIN 17 441
hot rolled	1U	hot rolled, not heat-treated, not quenched	free of scales	a1
	1C	hot rolled, not heat-treated, not quenched (pickled)		b (I c)
	1E	hot rolled, not heat-treated, (mechanically) quenched		d (II a)
	1D	hot rolled, not heat-treated, pickled		c2 (II a)
cold rolled	2H	to work-hardem	free of scales	f (II a)
	2C	cold rolled, heat-treated not quenched		
	2E	heat-treated, mechanically quenched, cold rolled		h (III b)
	2D	cold rolled, heat-treated, pickled		
	2B	cold rolled, heat-treated, pickled, lightly rerolled		n (III c)
	2R	cold rolled, bright annealed		
	2Q	cold rolled, bright annealed		m (III d)
special	1G or 2G	grinded	uniform finish	o (IV)
	1J or 2J	brushed or matt polished	planer than grinded	q
	1K or 2K	semi gloss polished	matt	p (V)
	1P or 2P	polished, bright polished	brigh	p (V)
	2F	cold rolled, heat-treated lightly rerolled with rough drums	matt, not-reflecting	
	1M or 2M	patterned	to be arraged	
	2W	corrugated	to be arraged	
	2L	inked	to be arraged	
	1S or 2S	surface coated	one-sided	